

POLYETHYLENE RESIN POWDER COMPOSITION FOR POWDER COATING

Patent Number: JP62270672
Publication date: 1987-11-25
Inventor(s): MATSUMOTO KOICHI; others: 01
Applicant(s):: ASAHI CHEM IND CO LTD
Requested Patent: JP62270672
Application Number: JP19860236100 19861006
Priority Number(s):
IPC Classification: C09D5/03 ; C09D3/733 ; C09D5/03 ; C09D5/30
EC Classification:
Equivalents: JP1649031C, JP3015946B

Abstract

PURPOSE:To provide the title compsn. which gives a coating film having a mottled pattern having a feeling of deepness, by blending two specified PE resin powders with (nucleus-substituted) dibenzylidenesorbitol.
CONSTITUTION:90-60pts.wt. PE resin powder (a) which has an MI of 5-100g/10min, a density of 0.910-0.935g/cc and a particle size of not larger than 500mu, whose sheet of 50mu in thickness has a haze of not higher than 30% and which is not colored, is mixed with 10-40pts.wt. two-color or multi-color PE resin powder (b) which has an MI of 1-500g/10min, a density of 0.910-0.970g/cc and a particle size of not larger than 1,000mu and is colored, to obtain a powder compsn. (A). 100pts.wt. component A is blended with 0.1-1.0 pts.wt. pref. 0.2-0.6pts.wt. (nucleus-substituted) dibenzylidenesorbitol (B) having the formula to obtain the title compsn. having a bulk density of 0.25-0.55g/cc, a particle size of not larger than 1,000mu and an angle of repose of 25-45 deg..


Data supplied from the esp@cenet database - I2

Patent Abstracts of Japan

PUBLICATION NUMBER : 62270672
PUBLICATION DATE : 25-11-87

APPLICATION DATE : 06-10-86
APPLICATION NUMBER : 61236100

APPLICANT : ASAHI CHEM IND CO LTD;



INVENTOR : YATANI HIROSHI;

INT.CL. : C09D 5/03 C09D 3/733 C09D 5/03
C09D 5/30

TITLE : POLYETHYLENE RESIN POWDER
COMPOSITION FOR POWDER
COATING

ABSTRACT : PURPOSE: To provide the title compsn. which gives a coating film having a mottled pattern having a feeling of deepness, by blending two specified PE resin powders with (nucleus-substituted) dibenzylidenesorbitol.

CONSTITUTION: 90~60pts.wt. PE resin powder (a) which has an MI of 5~100g/10min, a density of 0.910~0.935g/cc and a particle size of not larger than 500 μ , whose sheet of 50 μ in thickness has a haze of not higher than 30% and which is not colored, is mixed with 10~40pts.wt. two-color or multi-color PE resin powder (b) which has an MI of 1~500g/10min, a density of 0.910~0.970g/cc and a particle size of not larger than 1,000 μ and is colored, to obtain a powder compsn. (A). 100pts.wt. component A is blended with 0.1~1.0 pts.wt. pref. 0.2~0.6pts.wt. (nucleus-substituted) dibenzylidenesorbitol (B) having the formula to obtain the title compsn. having a bulk density of 0.25~0.55g/cc, a particle size of not larger than 1,000 μ and an angle of repose of 25~45°.

COPYRIGHT: (C)1987,JPO&Japio